



PBS SUPPLY CO.

7013 South 216th Street
Phone (253) 395-5550

Kent, WA 98032
Fax (253) 395-5575

WHITEBOARDS-BULLETINBOARDS-PROJECTION SCREENS-SPECIALTIES

Duracork Specifications

Binder Polymeric

Granule: 1-2 mm

Physical Characteristics

Specification

Density, Lbs./Cu.Ft.	11 min.
Tensile Strength, Psi	80 min.
Compressibility (100 psi),(%)	25 to 40%
Recovery, (%)	75% min.
Flexibility, (F-5)	No Cracks

Test Methods: Standard ASTM Mil-C-15116C, Type II

Note: A cork composition grade

Flammability	(E-84)
Rating	Class B
Smoke Developed	70
Flame Spread	65